In the Claims

The following listing of the claims replaces all previous listings.

- 1.-29. (Canceled)
- 30. (Currently Amended) [[An]] A compression molding composition for use in compression molding an article, said composition comprising:

in the range of greater than 0 to less than or equal to about 25 % or less by wt. inorganic fiber:

in the range of about 10 to 40 % by wt. binder; in the range of about 15 to 45 % by wt. carrier solvent; and in the range of about 0 to 70 % by wt. additional additives.

- 31. (Original) The composition of claim 30, wherein the binder is an inorganic binder.
- 32. (Currently Amended) The composition of claim 30, wherein the additional additives includes an inorganic filler, and the inorganic filler is in the range of 15 to 70_% by weight of the total composition.
- 33. (Currently Amended) The composition of claim 30, wherein the additional additives includes an organic polymer, and the organic polymer is in the range of 0.1 to 0.5 % by weight of the total composition.
- 34. (Original) The composition of claim 33, wherein the organic polymer is an acrylic polymer.
- 35. (Original) The composition of claim 33, wherein the organic polymer act as a molding thickener to help the composition hold shape when it is being molded.
- 36. (Original) The composition of claim 30, wherein the carrier solvent is water.

- 37. (Original) The composition of claim 36, wherein the composition has a moisture content in the range of 20 to 35% by weight of the total composition.
- 38. (Original) The composition of claim 37, wherein the composition has a moisture content 23 to 30% by weight of the total composition.
- 39. (Original) The composition of claim 38, wherein the composition has a moisture content in the range of 25 to 27% by weight of the total composition.